

R-420 – VeTron™ Roving

VeTron™ rovings are specifically designed and intended for filament wound or pre-impregnation applications requiring increased mechanical, physical, thermal, and electrical properties.

General Product Specifications

Product Information

Product	VE1-AB-1200	VE1-AB-2400
Glass Type	S-2	S-2
Binder	VE1	VE1
Compatibility*	PE, VE	PE, VE
Filament Diameter - μm	18	26
Package	4044 or 4144	4044 or 4144
Nominal Yield - yd/lb	413	207
Tex - g/1000 m	1204	2397
Tex Tolerance +/-	104	202
Nominal Solids - %	0.50	0.50
Solids Tolerance +/-	0.25	0.25
Maximum Moisture - %	0.06	0.06
Nominal Package Density - lb/in ³	0.060	0.054
Package Density Tolerance +/-	0.008	0.008
Minimum Impregnated Strand Tensile Strength - Ksi Mpa	300 (2068)	300 (2068)

Packaging Information

Package	4044 or 4144	4044 or 4144
Nominal Package Weight - lb (kg)	16.0 (7.25)	16.0 (7.25)
Minimum Package Weight - lb (kg)	8.0 (3.63)	8.0 (3.63)



Rev 5, 10.27.2020

* Compatibility is resin specific, please contact your AGY representative for more details.

R-420 – VeTron™ Roving

Nominal Packaging Dimensions

Fig	Product	Package	Packages / Layer	Layers / Carton	Cartons / Pallet	Packages / Pallet	L -in (cm)	W-in (cm)	H-in (cm)
1	VeTron VE1-AB-1200 VE1-AB-2400	4144	12	3	1	36	46.0 (116.8)	32.0 (81.3)	39.0 (99.1)
2		4044	20	3	1	60	45.5 (115.6)	45.5 (115.6)	37.0 (94.0)



Storage, Shelf Life and Handling

Storage and Shelf Life:

AGY recommends storing the materials in accordance with appropriate safety considerations, away from exposure to the elements and at 65-80F (18-27C) and 50-70% humidity. If the materials are stored under these conditions, they are stable, non reactive and will not degrade or exhibit negative characteristics for at least 3 years from the date of manufacture. Unused, unopened product older than this is likely still in good condition, however careful evaluation is recommended. Prior to use, pallets should be placed in the production area and any plastic wrap removed for a minimum of 24 hours to allow the material to acclimate to the processing environment. Special care should be given to pallets being moved from a cold environment into a warm, humid area as condensation may occur and this additional moisture can negatively impact the runability of the material, however, once the material has acclimated, this will no longer be an issue.

For product traceability reasons, the pallet label should be recorded or retained.

Handling:

Fiberglass products process best if temperature and humidity are controlled, primarily because this will help to minimize the buildup of static electricity, fuzz and fly. AGY recommends that the material be run at 70 +/- 5 degrees F (18-27C) and 60 +/- 5% RH.

Test Methods and Certificates

A copy of test methods and or a certificate of conformity may be issued upon request.

Packages will be firmly and evenly wound on the tube and free from defects in workmanship. AGY accepts no responsibility for damaged material that shows any signs of physical abuse.

For additional product information, refer to PTS M-711

AGY – World Headquarters / Americas

2556 Wagener Road
Aiken, South Carolina, USA 29801
Phone: +(1) 888.434.0945 (toll free)
+(1) 803.643.1501
Fax: +(1) 803.643.1180
Email: asktheexpert@agy.com

AGY – Europe

Le Gemellyon Nord
57 Boulevard Marius Vivier Merle
69003 Lyon, France
Phone: +(33) 4727 81775
Fax: +(33) 4727 81780